



# HexTow<sup>®</sup> AS4

## Carbon Fiber



### Product Data Sheet

HexTow<sup>®</sup> AS4 carbon fiber is a continuous, high strength, high strain, PAN based fiber available in 3,000 (3K), 6,000 (6K) and 12,000 (12K) filament count tows. This fiber has been surface treated and can be sized to improve its interlaminar shear properties, handling characteristics, and structural properties, and is suggested for use in weaving, prepregging, filament winding, braiding, and pultrusion.

AS4-GP 3k (1%), AS4-GP 12k (0.9%), and AS4 12k carbon fibers have been qualified to NMS 818 Carbon Fiber Specification (NCAMP). This allows customers to call out an industry standard, aerospace grade carbon fiber without the need to write and maintain their own specification.

Typical Fiber Properties	U.S. Units	SI Units
Tensile Strength	650 ksi	4501 Mpa
Tensile Modulus (Chord 6000-1000)	33.5 Msi	231 GPa
Ultimate Elongation at Failure	1.8%	1.8%
Density	0.0647 lb/in <sup>3</sup>	1.79 g/cm <sup>3</sup>
Weight/Length		
3K	11.8 x 10 <sup>-6</sup> lb/in	0.210 g/m
6K	23.9 x 10 <sup>-6</sup> lb/in	0.427 g/m
12K	48.0 x 10 <sup>-6</sup> lb/in	0.858 g/m
Approximate Yield		
3K	7,086 ft/lb	4.75 m/g
6K	3,485 ft/lb	2.34 m/g
12K	1,734 ft/lb	1.17 m/g
Tow Cross-Sectional Area		
3K	1.82 x 10 <sup>-4</sup> in <sup>2</sup>	0.12 mm <sup>2</sup>
6K	3.70 x 10 <sup>-4</sup> in <sup>2</sup>	0.24 mm <sup>2</sup>
12K	7.43 x 10 <sup>-4</sup> in <sup>2</sup>	0.48 mm <sup>2</sup>
Filament Diameter		
	0.280 mil	7.1 microns
Carbon Content		
	94.0%	94.0%
Twist		
	Never Twisted	Never Twisted

Typical HexPly 8552 Composite Properties (at Room Temperature)	U.S. Units	SI Units	Test Method
0° Tensile Strength	310 ksi	2137 MPa	ASTM D3039
0° Tensile Modulus	19.6 Msi	135 GPa	
0° Tensile Strain	1.6%	1.6%	
0° Flexural Strength	274 ksi	1889 MPa	ASTM D790
0° Flexural Modulus	18.4 Msi	127 GPa	
0° Short Beam Shear Strength	18.5 ksi	128 MPa	ASTM D2344
0° Compressive Strength	222 ksi	1530 MPa	ASTM Mod. D695
0° Compressive Modulus	18.6 Msi	128 GPa	
0° Open Hole Tensile Strength	63.5 ksi	438 MPa	ASTM D5766
90° Tensile Strength	9.3 ksi	64 MPa	ASTM D3039
Fiber Volume	60%	60%	



Yarn/Tow Characteristics	U.S. Units	SI Units
Specific Heat	0.28 Btu/lb-°F	0.27 cal/g-°C
Electrical Resistivity	$5.6 \times 10^{-5}$ ohm-ft	$1.7 \times 10^{-3}$ ohm-cm
Coefficient of Thermal Expansion	-0.35 ppm/°F	-0.63 ppm/°C
Thermal Conductivity	3.95 Btu/hr-ft-°F	6.83 W/m-°K

**Carbon Fiber Certification**

This carbon fiber is manufactured to Hexcel aerospace grade specification HS-CP-5000. A copy of this specification is available upon request. A Certification of Analysis will be provided with each shipment.

**Available Sizing**

Sizing compatible with various resin systems, based on application are available to improve handling characteristics and structural properties. Please see additional information on available sizes on our website or contact our technical team for additional information.

**Sizing**

Size	Compatibility	Recommended Uses
GP	Epoxy, Phenolic, Vinyl Ester, Polyurethane, Cyanate Ester, BMI	Weaving, Filament Winding, Prepreg Tape
G	Epoxy, Phenolic, Polyurethane	Weaving, Filament Winding, Prepreg Tape
Unsize	All Resins	Prepreg Tape

\*Compatibility with these Matrices is considered theoretically compatible. Hexcel cannot guarantee their results.

**Packaging**

Standard packaging of HexTow® AS4 is as follows:

Filament Count	Size	Nominal Weight		Nominal Length	
		(lb)	(kg)	(ft)	(m)
3K	G (1%)	5.0	2.3	35,430	10,800
	GP (1%)	6.0	2.7	42,520	12,960
6K	G (1%)	3.0	1.4	10,450	3,190
	GP (1%)	6.0	2.7	20,910	6,375
12K	GP (0.25%)	8.0	3.6	13,880	4,230
	GP (1%)				
	Unsize	10.0	4.5	17,340	5,290

Other package sizes may be available on request. The fiber is wound on a 3-inch ID by 11-inch long cardboard tube and overwrapped with plastic film.

**Safety Information**

Obtain, read, and understand the Safety Data Sheet (SDS) before use of this product.



## For more information

Hexcel is a leading worldwide supplier of composite materials to aerospace and industrial markets. Our comprehensive range includes:

- HexTow® carbon fibers
- HexForce® reinforcements
- HiMax® multiaxial reinforcements
- HexPly® prepregs
- HexAM® additive manufacturing
- HexMC® molding compounds
- HiFlow® RTM resins
- HexBond® adhesives
- HexTool® tooling materials
- HexWeb® honeycomb
- Acousti-Cap® sound attenuating honeycomb
- Engineered core
- Engineered products
- Polyspeed® laminates & pultruded profiles

For U.S. quotes, orders and product information call toll-free 1-800-688-7734. For other worldwide sales office telephone numbers and a full address list, please go to:

**<http://www.hexcel.com/contact>**

©2023 Hexcel Corporation – All rights reserved. Hexcel Corporation and its subsidiaries ("Hexcel") believe that the technical data and other information provided herein was materially accurate as of the date this document was issued. Hexcel reserves the right to update, revise or modify such technical data and information at any time. Any performance values provided are considered representative but do not and should not constitute a substitute for your own testing of the suitability of our products for your particular purpose. Hexcel makes no warranty or representation, express or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose, and disclaims any liability arising out of or related to, the use of or reliance upon any of the technical data or information contained in this document.