

Technical Data Sheet

DD-13230




Description

- Flexible, loaded silicone magnetic absorber.
- Highly conductive absorber that provides excellent shielding over a wide frequency range.
- Standard Sheet Size:
 - 12" x 12" (30.48 cm x 30.48 cm)
 - Custom sheet sizes available upon request.
- Available with pressure sensitive adhesive (PSA).
- Can be water-jet or die cut for custom configurations.
- Halogen free, RoHS and REACH compliant.

Properties	Test Method	Value
Durometer	ASTM D2240	67 Shore A
Tensile Strength	ASTM D638	250 psi
Elongation	ASTM D638	381%
Surface Resistivity	ASTM D257	4.2 Ω/□
Max Operating Temperature	--	375°F (190°C)
Flammability Rating	--	UL94 V-0
Standard Sheet Thickness	--	0.045" (1.143 mm) Other thicknesses available upon request.
Color	--	Gray

Insertion Loss



Note: the information provided above is accurate at time of publication. It is the responsibility of the end-user to confirm compliance to their application. All test data is typical.