



# HexBond™ EA9392 STRUCTIL

## Two-component epoxy paste adhesive



### Product Data Sheet

#### Description

Thixotropic two-component epoxy adhesive. Its viscosity allows for it to be used for structural bonding, potting, filling, liquid shim and fairing applications. HexBond™ EA9392 STRUCTIL is the toughened version of HexBond™ EA9394 STRUCTIL.

#### Features

- Room temperature curing ( $\geq 18^{\circ}\text{C}/64^{\circ}\text{F}$ )
- Excellent mechanical properties at temperatures ranging from  $-55^{\circ}\text{C}/-67^{\circ}\text{F}$  to  $180^{\circ}\text{C}/356^{\circ}\text{F}$
- Good toughness

#### Uncured Adhesive Properties

	Part A	Part B	Mixture
Colour	Grey	Amber	Grey
Brookfield viscosity at $23^{\circ}\text{C}$ / $73^{\circ}\text{F}$ (Poise)	2000 to 6000	3000 to 7000	
Density ( $\text{g}/\text{cm}^3$ )	1.4	1.0	
Standard shelf-life at $\leq 23^{\circ}\text{C}$ / $73^{\circ}\text{F}$ (From date of shipment)	1 year	1 year	

#### Instructions For Use:

Refer to the Material Safety Data Sheet before handling.

Mixing: Mix ration by weight: Part A/Part B: 100/32

Thoroughly mix the two parts until the resulting colour is a consistent grey.

Do not mix quantities greater than 450g as dangerous heat build-up can occur.

Pot-life: Pot-life of 100g mass (Part A + B) at  $23^{\circ}\text{C}/73^{\circ}\text{F} \approx 130$  minutes

Bonding surfaces should be clean, dry and properly prepared.

Curing: 3 to 5 days at  $23^{\circ}\text{C}/73^{\circ}\text{F}$  to achieve optimal performance

It is possible to reduce the polymerisation time by heating at a maximum temperature of  $93^{\circ}\text{C}/200^{\circ}\text{F}$ . The product must be kept at least 4 hours at room temperature prior to testing. For example, 60 minutes at  $65^{\circ}\text{C}/150^{\circ}\text{F}$  to obtain the best performance.



# HexBond™ EA9392 STRUCTIL

## Two-component epoxy paste adhesive



### Product Data Sheet

#### Bond Strength Performance After Cure

Test Temperature (°C / °F)	Shear <sup>(1)</sup> : Lap Shear Strength (MPa / psi)	Peel <sup>(2)</sup> : Bell Peel Strength (N/25mm)
23 / 73	29 / 4200	150
80 / 176	20 / 2900	
121 / 250	17 / 2465	
150 / 302	10 / 1450	

(1) According to EN 2243-1, on aluminum 2024T3 clad treated with sulfo-chromic acid etch, cured 5 days at 23°C/73°F

(2) According to EN 2243-2, on aluminum 2024T3 clad treated with sulfochromic acid etch, cured 5 days at 23°C/73°F

This information is provided for informal purposes only, without legal responsibility and does not constitute a specification. Users are expected to perform adequate verification and testing to ensure that materials meet required specification.

#### For more information

Hexcel is a leading worldwide supplier of composite materials to aerospace and industrial markets. Our comprehensive range includes:

- HexTow® carbon fibers
- HexForce® reinforcements
- HiMax™ multiaxial reinforcements
- HexPly® prepgs
- HexAM™ additive manufacturing
- HexMC® molding compounds
- HexFlow® RTM resins
- HexBond™ adhesives
- HexTool® tooling materials
- HexWeb® honeycombs
- Acousti-Cap® sound attenuating honeycomb
- Engineered core
- Engineered products
- Polyspeed™ laminates

For US quotes, orders and product information call toll-free 1-800-688-7734. For other worldwide sales office telephone numbers and a full address list, please go to:

<http://www.hexcel.com/contact/salesoffice>

©2019 Hexcel Corporation – All rights reserved. Hexcel Corporation and its subsidiaries (“Hexcel”) believe that the technical data and other information provided herein was materially accurate as of the date this document was issued. Hexcel reserves the right to update, revise or modify such technical data and information at any time. Any performance values provided are considered representative but do not and should not constitute a substitute for your own testing of the suitability of our products for your particular purpose. Hexcel makes no warranty or representation, express or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose, and disclaims any liability arising out of or related to, the use of or reliance upon any of the technical data or information contained in this document.

