



HexBond™ EA9674 STRUCTIL BMI Adhesive Film



Product Data Sheet

Description

Hexbond™ EA9674 is an epoxy/bismaleimide film adhesive designed for high temperature bonding application. It is specially recommended for metal/metal or composite/metal bonding and for co-curing of sandwich structures.

Features

- Outstanding mechanical properties over a wide range of temperature (-55°C/-67°F to 210°C/410°F)
- Can be reticulate on acoustic panel
- Storage life: 1 year at or below -18°C/0°F +2 weeks at room temperature ($\leq 23^\circ\text{C}/73^\circ\text{F}$)

Applications

- Metal-to-metal bonding
- Sandwich construction
- Composite-to-composite bonding


Uncured Adhesive Properties

	Areal Weight (g/m ²)	Support	Roll Width (mm)	Standard Roll m ²
EA9674.06 UNS	300	None	500	15
EA9674.06 GLS	300	Glass fabric	500	25

Instructions For Use

Refer to the Safety Data Sheet before handling.

- To avoid any moisture, allow the adhesive to warm at room temperature before opening the waterproof polyethylene bag
- Bonding surfaces should be clean, dry and properly prepared
- Remove protective liners before bonding (release paper and polyethylene film)
- Typical cure cycles: 1h at 180°C/356°F under pressure + 6h at 230°C/446°F without pressure
Heat up rate: 1 to 4°C/min
Pressure: 1.5 to 3.5 bar





Bond Strength Performance After Cure

Test	Test Temperature (°C / °F)	EA9674.06 UNS	EA9674.06 GLS
Simple lap shear strength ⁽¹⁾ (MPa / psi)	23 / 73	31.4 / 4550	30.4 / 4400
	180 / 356	30.5 / 4400	28.4 / 4100
	230 / 446	-	14.0 / 2030
	250 / 482	-	6.1 / 880
Honeycomb climbing drum peel torque ⁽²⁾ (mN/m)	23 / 73	23.9	22.7
Flatwise tension strength ⁽³⁾ (MPa / psi)	23 / 73	7.7 / 1100	7.7 / 1100

Cure: 1h at 140°C (284°F) + 3h at 190°C (374°F) under 2.5 bar + post cure: 8h at 230°C (446°F) without pressure/heat up/cool down rate: 1.5°C/min

⁽¹⁾ According to EN 2243-1, on aluminum 2024T3 clad treated with sulfo-chromic acid etch

⁽²⁾ According to EN 2243-3, on aluminum 2024T3 clad treated with sulfo-chromic acid etch, honeycomb core aluminum PAA 5052 N 6.0 1/4, 16mm high, unslotted

⁽³⁾ According to EN 2243-4, on aluminum 2024T3 clad treated with sulfo-chromic acid etch, honeycomb core aluminum PAA 5052 N 6.0 1/4, 16mm high, unslotted

The information is provided for informal purposes only, without legal responsibility and does not constitute a specification. Users are expected to perform adequate verification and testing to ensure that materials meet required specification.

For more information

Hexcel is a leading worldwide supplier of composite materials to aerospace and industrial markets. Our comprehensive range includes:

- HexTow® carbon fibers
- HexForce® reinforcements
- HiMax™ multiaxial reinforcements
- HexPly® preprints
- HexAM™ additive manufacturing
- HexMC® molding compounds
- HexFlow® RTM resins
- HexTool® tooling materials
- HexWeb® honeycombs
- HexBond™ adhesives
- Acousti-Cap® sound attenuating honeycomb
- Engineered core
- Engineered products
- Polyspeed™ laminates

For US quotes, orders and product information call toll-free 1-800-688-7734. For other worldwide sales office telephone numbers and a full address list, please go to:

<http://www.hexcel.com/contact/salesoffice>

©2019 Hexcel Corporation – All rights reserved. Hexcel Corporation and its subsidiaries (“Hexcel”) believe that the technical data and other information provided herein was materially accurate as of the date this document was issued. Hexcel reserves the right to update, revise or modify such technical data and information at any time. Any performance values provided are considered representative but do not and should not constitute a substitute for your own testing of the suitability of our products for your particular purpose. Hexcel makes no warranty or representation, express or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose, and disclaims any liability arising out of or related to, the use of or reliance upon any of the technical data or information contained in this document.

