



HexTow® IM2C

Carbon Fiber



Product Data Sheet

HexTow® IM2C carbon fiber is a continuous, high performance, intermediate modulus, PAN based fiber available in 12,000 (12K) filament count tows. This fiber has been surface treated and can be sized to improve its interlaminar shear properties, handling characteristics, and structural properties. It is suggested for use in prepegging, filament winding, braiding, and pultrusion.

The unique properties of HexTow® IM2C fiber, such as higher tensile strength and modulus, as well as good shear strength, allow structural designers to achieve both higher safety margins for both stiffness and strength critical applications. HexTow® IM2C is International Monohull Open Class Association (IMOCA) certified/qualified.

Typical Fiber Properties	U.S. Units	SI Units
Tensile Strength (12K)	830 ksi	5,723 MPa
Tensile Modulus (Chord 6000-1000)	43 Msi	296 GPa
Ultimate Elongation at Failure (12K)	1.8%	1.8%
Density	0.0643 lb/in ³	1.78 g/cm ³
Weight/Length (12K)	25.0 x 10 ⁻⁶ lb/in	0.446 g/m
Approximate Yield (12K)	3,337 ft/lb	2.24 m/g
Tow Cross-Sectional Area (12K)	3.89 x 10 ⁻⁴ in ²	0.25 mm ²
Filament Diameter	0.203 mil	5.2 microns
Carbon Content	95.0%	95.0%
Twist	Never Twisted	Never Twisted

Carbon Fiber Certification

This carbon fiber is manufactured to Hexcel industrial specification HS-CP-3000. A copy of this specification is available upon request. A Certification of Conformance will be provided with each shipment.

Available Sizing

Sizing compatible with various resin systems, based on application are available to improve handling characteristics and structural properties. Please see additional information on available sizes on our website or contact our technical team for additional information.

Sizing

Size	Compatibility	Recommended Uses
GS	Epoxy, Vinyl Ester, Polyurethane	Prepreg Tape

*Compatibility with these Matrices is considered theoretically compatible. Hexcel cannot guarantee their results.



Packaging

Standard packaging of HexTow® IM2C is as follows:

Filament Count	Sizing	Nominal Weight		Nominal Length	
		(lb)	(kg)	(ft)	(m)
12K	GS (0.5%)	8.0	3.6	26,670	8,130

Other package sizes may be available on request. The fiber is wound on a 3-inch ID by 11-inch long cardboard tube and overwrapped with plastic film.

Safety Information

Obtain, read, and understand the Safety Data Sheet (SDS) before use of this product.

For more information

Hexcel is a leading worldwide supplier of composite materials to aerospace and industrial markets.

Our comprehensive range includes:

- HexTow® carbon fibers
- HexForce® reinforcements
- HiMax® multiaxial reinforcements
- HexPly® preprints
- HexAM® additive manufacturing
- HexMC® molding compounds
- HiFlow® RTM resins
- HexBond® adhesives
- HexTool® tooling materials
- HexWeb® honeycomb
- Acousti-Cap® sound attenuating honeycomb
- Engineered core
- Engineered products
- Polyspeed® laminates & pultruded profiles

For U.S. quotes, orders and product information call toll-free 1-800-688-7734. For other worldwide sales office telephone numbers and a full address list, please go to:

<http://www.hexcel.com/contact>

©2023 Hexcel Corporation – All rights reserved. Hexcel Corporation and its subsidiaries ("Hexcel") believe that the technical data and other information provided herein was materially accurate as of the date this document was issued. Hexcel reserves the right to update, revise or modify such technical data and information at any time. Any performance values provided are considered representative but do not and should not constitute a substitute for your own testing of the suitability of our products for your particular purpose. Hexcel makes no warranty or representation, express or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose, and disclaims any liability arising out of or related to, the use of or reliance upon any of the technical data or information contained in this document.