



HexTow[®] IM7

Carbon Fiber



Product Data Sheet

HexTow[®] IM7 carbon fiber is a continuous, high performance, intermediate modulus, PAN based fiber available in 12,000 (12K) filament count tows. This fiber has been surface treated and can be sized to improve its interlaminar shear properties, handling characteristics, and structural properties. It is suggested for use in weaving, prepregging, filament winding, braiding, and pultrusion.

The unique properties of HexTow[®] IM7 fiber, such as higher tensile strength and modulus, as well as good shear strength, allow structural designers to achieve both higher safety margins for both stiffness and strength critical applications.

IM7-G 12K (0.25%) carbon fiber has been qualified to NMS 818 Carbon Fiber Specification (NCAMP). This allows customers to call out an industry standard, aerospace grade carbon fiber without the need to write and maintain their own specification.

Typical Fiber Properties	U.S. Units	SI Units
Tensile Strength	820 ksi	5670 MPa
Tensile Modulus (Chord 6000-1000)	40.0 Msi	276 GPa
Ultimate Elongation at Failure	1.8%	1.8%
Density	0.0643 lb/in ³	1.78 g/cm ³
Weight/Length		
6K	12.5 x 10 ⁻⁶ lb/in	0.223 g/m
12K	25.0 x 10 ⁻⁶ lb/in	0.446 g/m
Approximate Yield		
6K	6,674 ft/lb	4.48 m/g
12K	3,337 ft/lb	2.24 m/g
Tow Cross-Sectional Area		
6K	1.94 x 10 ⁻⁴ in ²	0.13 mm ²
12K	3.89 x 10 ⁻⁴ in ²	0.25 mm ²
Filament Diameter		
0.203 mil		5.2 microns
Carbon Content		
95.0%		95.0%
Twist		
Never Twisted		Never Twisted

Typical HexPly 8552 Composite Properties (at Room Temperature)	U.S. Units	SI Units	Test Method
0° Tensile Strength	395 ksi	2,723 MPa	ASTM D3039
0° Tensile Modulus	23.8 Msi	164 GPa	
0° Tensile Strain	1.6%	1.6%	
0° Flexural Strength	270 ksi	1,862 MPa	ASTM D790
0° Flexural Modulus	22.0 Msi	152 GPa	
0° Short Beam Shear Strength	18.5 ksi	128 MPa	ASTM D2344
0° Compressive Strength	245 ksi	1,689 MPa	ASTM Mod. D695
0° Compressive Modulus	21.7 Msi	150 GPa	
Open Hole Tensile Strength	62.1 ksi	428 MPa	ASTM D5766
Open Hole Compressive Strength	48.9 ksi	337 MPa	ASTM D6484
90° Tensile Strength	9.3 ksi	64.1 MPa	ASTM D3039
Fiber Volume	60%	60%	



Yarn/Tow Characteristics	U.S. Units	SI Units
Specific Heat	0.21 Btu/lb-°F	0.21 cal/g-°C
Electrical Resistivity	4.9×10^{-5} ohm-ft	1.5×10^{-3} ohm-cm
Coefficient of Thermal Expansion	-0.36 ppm/°F	-0.64 ppm/°C
Thermal Conductivity	3.12 Btu/hr-ft-°F	5.40 W/m-°K

Carbon Fiber Certification

This carbon fiber is manufactured to Hexcel aerospace grade specification HS-CP-5000. A copy of this specification is available upon request. A Certification of Analysis will be provided with each shipment.

Available Sizing

Sizing compatible with various resin systems, based on application are available to improve handling characteristics and structural properties. Please see additional information on available sizes on our website or contact our technical team for additional information.

Sizing

Size	Compatibility	Recommended Uses
GP	Epoxy, Phenolic, Vinyl Ester, Polyurethane, Cyanate Ester, BMI	Weaving, Filament Winding, Prepreg Tape
G	Epoxy, Phenolic, Polyurethane	Weaving, Prepreg Tape
Unsize	All Resins	Prepreg Tape

**Compatibility with these Matrices is considered theoretically compatible. Hexcel cannot guarantee their results.*

Yarn/Tow Characteristics	U.S. Units	SI Units
Specific Heat	0.21 Btu/lb-°F	0.21 cal/g-°C
Electrical Resistivity	4.9×10^{-5} ohm-ft	1.5×10^{-3} ohm-cm
Coefficient of Thermal Expansion	-0.36 ppm/°F	-0.64 ppm/°C
Thermal Conductivity	3.12 Btu/hr-ft-°F	5.40 W/m-°K

Carbon Fiber Certification

This carbon fiber is manufactured to Hexcel aerospace grade specification HS-CP-5000. A copy of this specification is available upon request. A Certification of Analysis will be provided with each shipment.

Available Sizing

Sizing compatible with various resin systems, based on application are available to improve handling characteristics and structural properties. Please see additional information on available Sizes on our website or contact our technical team for additional information.

**Packaging**

Standard packaging of HexTow® IM7 is as follows:

Filament Count	Sizing	Nominal Weight		Nominal Length	
		(lb)	(kg)	(ft)	(m)
6K	GP (1%)	5.0	2.3	33,330	10,160
12K	Unsize	4.0	1.8	13,330	4,060
	G (0.25%)	8.0	3.6	26,670	8,130
	GP (0.9%)				

Other package sizes may be available on request. The fiber is wound on a 3-inch ID by 11-inch long cardboard tube and overwrapped with plastic film.

Safety Information

Obtain, read, and understand the Safety Data Sheet (SDS) before use of this product.

For more information

Hexcel is a leading worldwide supplier of composite materials to aerospace and industrial markets. Our comprehensive range includes:

- HexTow® carbon fibers
- HexForce® reinforcements
- HiMax® multiaxial reinforcements
- HexPly® prepregs
- HexAM® additive manufacturing
- HexMC® molding compounds
- HiFlow® RTM resins
- HexBond® adhesives
- HexTool® tooling materials
- HexWeb® honeycomb
- Acousti-Cap® sound attenuating honeycomb
- Engineered core
- Engineered products
- Polyspeed® laminates & pultruded profiles

For U.S. quotes, orders and product information call toll-free 1-800-688-7734. For other worldwide sales office telephone numbers and a full address list, please go to:

<http://www.hexcel.com/contact>

©2023 Hexcel Corporation – All rights reserved. Hexcel Corporation and its subsidiaries ("Hexcel") believe that the technical data and other information provided herein was materially accurate as of the date this document was issued. Hexcel reserves the right to update, revise or modify such technical data and information at any time. Any performance values provided are considered representative but do not and should not constitute a substitute for your own testing of the suitability of our products for your particular purpose. Hexcel makes no warranty or representation, express or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose, and disclaims any liability arising out of or related to, the use of or reliance upon any of the technical data or information contained in this document.